

Technical Data Sheet

Material Designation

B-95

Material Properties
Summary

- Binderless* *Organic Binder* *Double Laminated*
 Acrylic Binder *Laminated* *Hydrophobic*

This is a very high efficiency particulate filter medium especially suited to applications requiring a high degree of filtration in either gases or liquids. This material is composed of borosilicate glass microfibers with an acrylic resin. It exhibits excellent strength properties.

Micron rating

1

μm

Basis Weight

47

lbs/3,000 ft²
TAPPI Method T410

Caliper Thickness

0.016

inches - 4 psi
TAPPI Method T411

Mean Pore Size

2.7

μm

DOP Smoke Penetration

0.000

% at 0.3 μm @
10.5 ft/minute

ASTM Method D-2986

Air Flow Resistance

52.5

mm H₂O @
10.5 ft/minute
ASTM Method D-2986

Tensile Strength MD

7.0

lbs / inches
TAPPI Method T494

Tensile Strength CD

4.0

lbs / inches
TAPPI Method T494

Dry Elongation MD

2.0

%

TAPPI Method T494

Dry Elongation CD

2.0

%

TAPPI Method T494

Frazier Permeability

-

ft³ / min / ft² @
0.5in H₂O W.G.

ASTM Method F778-82

Gurley Stiffness

700

mg

TAPPI Method T543

Water Repellency

-

Inches H₂O

Ignition Loss

5.0

% Loss

Comments:

Actual filtration performance, i.e. efficiency and dust holding capacity, will vary depending upon filter design parameters and the normal variation of the media properties consistent with the specification range. We continuously strive to define our products and hence the specifications are subject to change.